

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C07C 53/126, C08K 5/09, C07C 53/128		A1	(11) International Publication Number: WO 95/34524
			(43) International Publication Date: 21 December 1995 (21.12.95)
(21) International Application Number: PCT/EP95/02247			(81) Designated States: CA, CN, JP, KR, SG, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(22) International Filing Date: 8 June 1995 (08.06.95)			
(30) Priority Data: 9411698.5 10 June 1994 (10.06.94) GB			
(71) Applicant (for all designated States except US): EXXON CHEMICAL PATENTS INC. [US/US]; 1900 East Linden Avenue, Linden, NJ 07036 (US).			
(72) Inventors; and (75) Inventors/Applicants (for US only): REYNIERS, Sylvain, Leontina, Edmond [BE/BE]; Peter Benoitlaan 2, B-1880 Kapelle-op-den-Bos (BE). HYNA, Viktor [DE/BE]; Hebronlaan 83, B-1831 Kraainem (BE).			
(74) Agents: BAWDEN, Peter, Charles et al.; Exxon Chemical Limited, Exxon Chemical Technology Centre, P.O. Box 1, Abingdon, Oxfordshire OX13 6BB (GB).			
(54) Title: BASIC ZINC CARBOXYLATES			
(57) Abstract Superbase zinc soaps in the form of zinc carboxylates, in which the carboxylic acids consisting of a mixture or otherwise of saturated organic carboxylic acids containing from 7 to 13 carbon atoms, having the following characteristics: a linear acid content of between 0 and 40 % by weight, a content of acids which are branched on carbon 2 of between 0 and 20 % by weight, and a content of acids which are mono- or polysubstituted on carbon 3 and/or on the carbons of higher rank, which is equal to or greater than 50 % by weight; their preparation and use as polymer stabilisers particularly for polyvinyl chloride.			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

BASIC ZINC CARBOXYLATES.

The present invention relates to new basic zinc carboxylate, both liquid and solid compositions, a method for their preparation and their use as lubricant additives,
5 as polymer stabilisers, as promoters or emulsifiers for rubber and fungicides. In particular the invention provides an effective stabiliser for use in polyvinyl chloride which may replace the more toxic Cadmin, Lead and Barium stabilisers currently used.

10 Basic zinc carboxylates are known in many forms and are commonly used as polymer stabilisers.

It is desirable to have as high a zinc level as possible in these products to reduce the amount of additive required to provide the desired zinc level. It has however
15 proved difficult to develop a commercial process for the production of high zinc content zinc carboxylates.

There is therefore a need for a high solid content or 100% solid basic zinc carboxylate which may be incorporated into polymers, particularly as a stabiliser
20 for polyvinyl chloride without an adverse effect of the viscosity of the polymer to enable better handling.

We have now found that high zinc contents may be obtained when the various carboxylic acid mixtures described in European Patent 234149 are used as raw
25 materials.

We have now developed new solid zinc superbase soaps which do not possess the disadvantages of the known superbase soaps, which have a high metal content of the order of 15% to 35%, typically 20% to 30% or even higher, and
30 which yield perfectly stable and clear solutions when employed.

The present invention therefore provides solid zinc superbase soaps in the form of zinc carboxylates, the carboxylic acids consisting of a mixture or otherwise of saturated organic carboxylic acids containing from 7 to 13 carbon atoms, having
35 the following characteristics, optionally the products may also contain zinc carbonate.

- a linear acid content of between 0 and 40% by weight,
- a content of acids which are branched on carbon 2 of between 0 and 20% by weight, and
- 5 • a content of acids which are mono- or polysubstituted on carbon 3 and/or on the carbons of higher rank, which is equal to or greater than 50% by weight.

10 The zinc superbase soaps are preferably prepared from saturated C₈, C₉ and C₁₀ organic carboxylic acids which consist of isomeric mixtures and which are generally known as oxo acids. These oxo acids are characterized by a low linear acid content, generally less than or equal to 10% by weight, a low content of acids which are branched on carbon 2, generally less than or equal to 10% by weight, and a high content of acids which are mono- or polysubstituted on carbon 15 3 and/or carbons of higher rank, which is generally greater than 80% by weight. The oxo acids are obtained by hydroformylation of C₇, C₈ and C₉ olefins, followed by an oxidation.

20 Still more preferably, the zinc soaps according to the invention are prepared from the C₈ saturated carboxylic acid (that is containing 8 carbon atoms) marketed under the trademark Cekanoic, this acid consisting of an isomeric mixture of octanoic acids containing at most 10% by weight of n-octanoic acid, at most 10% by weight of C₈ acids which are branched on carbon 2 and at least 80% by weight of C₈ acids which are branched on carbon 3 and/or the carbons of higher 25 rank. In fact, it has surprisingly been found that the use of this acid makes it possible to obtain zinc soaps with a very high zinc content of the order of 25% or higher. Still more preferably it is made from the similar material known as Cekanoic C₁₀ acid.

30 Among the organic carboxylic acids which are also suitable for the present invention there may also be added the derivatives which are mono- or polysubstituted in the 3-position and/or of higher rank of the acids corresponding to heptanoic acid, octanoic acid, nonanoic acid, decanoic acid, undecanoic acid and dodecanoic acid. These include, for example, 3-methylhexanoic acid, 35 isooctanoic acid, 4,5-dimethylhexanoic acid, isononanoic acid, 3,5,5-trimethylhexanoic acid, isodecanoic acid, 3-ethyloctanoic acid, isoundecanoic acid, 4-ethylnonanoic acid and isododecanoic acid. The mixture

of one or more of the above-mentioned acids, whether mixed or not with their isomers, is also suitable for the present invention, it being understood that the content of linear acids does not exceed 40% and that the content of acids which are substituted on carbon 2 does not exceed 20%. We have found, in fact, that
5 the linear acids and that the acids branched on carbon 2 lead to the formation of a viscous product, or to setting solid or, alternatively, to a precipitate which renders the product practically useless.

The present invention also relates to a process for the preparation of the zinc
10 superbase soaps described above, according to which a zinc oxide and/or hydroxide is reacted with the appropriate acid, with stirring. In a further embodiment the reaction may include the addition of carbon dioxide (CO₂) which is bubbled through the reaction mixture and at least one organic carboxylic acid, in the presence of at least one promoter which make CO₂ fixation easier and at
15 least one catalyst, and in that the water formed during the reaction is removed. In this aspect of the invention the process is characterized in that the reaction is performed in at least one organic solvent at a temperature of between 80 and 120°C, and in that the said acid is a saturated organic carboxylic acid containing from 7 to 13 carbon atoms, in which the content of linear acids is less than or
20 equal to 40% by weight, in which the content of acids branched on carbon 2 is less than or equal to 20% by weight, and in which the content of acids branched on carbon 3 and/or the carbons of higher rank is equal to or higher than 40% by weight.

25 When the reaction has ended, after filtration, the organic solvent may be removed preferably by evaporation.

In accordance with a preferred embodiment of the process according to the invention, the organic solvent is allowed to evaporate during the reaction and is
30 recycled into the reaction mixture so as to produce therein a bubbling action which promotes the reaction. Alternatively, a plasticiser ester such as a phthalate or adipate may be used as the solvent which is particularly useful when the zinc carboxylate is to be used as a stabiliser for polyvinyl chloride.

35 At least one nonpolar organic solvent chosen from naphtha, hexane, kerosene, benzene, toluene or xylene is used among the organic solvents which can be used in the process according to the invention. It is also possible to use a

mixture of paraffinic hydrocarbons of mineral or synthetic origin, preferably containing a low proportion of aromatic and/or naphthenic hydrocarbons, such as white spirit. It is also possible to consider the use of polar organic solvents such as alcohols, for example 1-butanol, 2-butanol, ethylene glycol, propylene glycol, 5 ethylene glycol monomethyl ether, ethylene glycol dimethyl ether, diethylene glycol and its ethers, mixtures of alcohols derived from paraffin, or methyl ethyl ketone.

10 The molar ratio of zinc to the organic carboxylic acid employed in the reaction is generally between 0.55 and 2, which corresponds to a basicity of between 1.1 and 4.

It should be recalled that the basicity is equal to the ratio of equivalents of zinc to the equivalents of carboxylic acids which are employed.

15 Where carbon dioxide is used an hourly flow rate of carbon dioxide is imposed such that the hourly mass ratio of carbon dioxide to zinc is between 0.5 and 2, and preferably between 0.7 and 1.5.

20 Among the catalysts which may be used in the process according to the invention there may be mentioned metal oxides, for example, aluminium oxide Al_2O_3 , silver oxide Ag_2O , magnesium oxide MgO , and zinc carboxylates such as zinc octanoate.

25 When CO_2 is used among the promoters which made CO_2 fixation easier and which can be used in the present invention there may be mentioned labile hydrogen compounds such as alcohols, for example methanol, 2-propanol, octyl alcohol, ethylene glycol, triethylene glycol, stearyl alcohol, cyclohexylene glycol alcohol, cyclohexyl alcohol, aromatic alcohols such as phenol; amines, for 30 example aniline, phenylenediamine, or dodecylamine; or, yet again, a mixture of alcohols and/or amines, for example of methanol and aqueous ammonia.

However, preferably, the material used is methanol, which gives the highest basicities and the shortest filtration times during the preparation of the calcium 35 soap according to the invention.

In the superbase soaps according to the invention, the promoters are used in a proportion of 1 to 25% by weight of final zinc salt, and preferably in a proportion of 5 to 15%.

- 5 The present invention will be better understood by reading the nonlimiting examples of the invention which follow.

Example 1:

- 94.1 g Zinc Oxide (having a minimum purity of 99.5%) and 123.3 g Diisononyl
10 phthalate were loaded into a reactor and stirred vigorously for 15 minutes.
Over a period of 45 minutes 298.3 g Cekanoic C₁₀ acid is added and the
temperature raised to 27°C, the heater was then set at 30°C and the exothermic
reaction quickly took the temperature to 52°C.
The solution was slowly heated to 165°C to remove the water from the reactor
15 and maintained at 165°C until no more water comes over.

Example 2

- 93.9g of the Zinc Oxide used in Example and 127.3 g Diisononyl phthalate were
loaded into a reactor and stirred vigorously for 15 minutes.
20 Over a period of 45 minutes 298.2 g 298.2 g Cekanoic C₁₀ acid is added and the
temperature raised to 27°C, the heater was set at 30°C and the exothermic
reaction took the temperature quickly to 52°C.
The solution was slowly heated to 110°C and then put vacuum on it to remove
the water from the reactor. Filtration was carried out at 110°C to yield the end
25 product as a viscous light yellow liquid.

Example 3

- 93.8 g of the Zinc Oxide used in Example 1 and 123.6 g Toluene were loaded
into a reactor and stirred vigorously for 15 minutes.
30 Over a period of 45 minutes 298.9 g Cekanoic C₁₀ acid is added and the
temperature raised to 40°C. The solution is then slowly heated to 129°C to
remove the water from the reactor and maintained at 129°C until no more water
comes over.
The end product is a clear product.
35 The Toluene is evaporated and a white solid paste is formed.

Claims:

1. Solid zinc superbase soaps in the form of zinc carboxylates, the carboxylic acids consisting of a mixture or otherwise of saturated organic carboxylic acids containing from 7 to 13 carbon atoms, having the following characteristics:
 - a linear acid content of between 0 and 40% by weight,
 - a content of acids which are branched on carbon 2 of between 0 and 20% by weight, and
 - a content of acids which are mono- or polysubstituted on carbon 3 and/or on the carbons of higher rank, which is equal to or greater than 50% by weight.
2. The zinc superbase soaps of claim 1 prepared from saturated isomeric mixtures of C₈, C₉ and C₁₀ organic carboxylic acids.
3. The zinc soap of claim 2 in which the oxo acids are characterized by a low linear acid content, generally less than or equal to 10% by weight, a low content of acids which are branched on carbon 2, generally less than or equal to 10% by weight, and a high content of acids which are mono- or polysubstituted on carbon 3 and/or carbons of higher rank, which is generally greater than 80% by weight.
4. A process for the preparation of the zinc superbase soaps according to any of claims 1 to 3, according to which a zinc oxide and/or hydroxide is reacted, with stirring, with carbon dioxide (or CO₂) which is bubbled through the reaction mixture and at least one organic carboxylic acid, in the presence of at least one promoter which makes CO₂ fixation easier and at least one catalyst, and in that the water formed during the reaction is removed.
5. A process according to claim 4 is characterized in that the reaction is performed in at least one organic solvent at a temperature of between 80 and 120°C, and in that the said acid is a saturated organic carboxylic acid

5 containing from 7 to 13 carbon atoms, in which the content of linear acids is less than or equal to 40% by weight, in which the content of acids branched on carbon 2 is less than or equal to 20% by weight, and in which the content of acids branched on carbon 3 and/or the carbons of higher rank is equal to or higher than 40% by weight.

6. A process according to claim 4 or claim 5 in which the organic solvent is allowed to evaporate during the reaction and is recycled into the reaction mixture so as to produce therein a bubbling action which promotes the
10 reaction.

7. The use of a superbases zinc soap according to any of claims 1 to 4 as a stabiliser for polyvinyl chloride.

INTERNATIONAL SEARCH REPORT

Intern. Application No
PCT/EP 95/02247

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C07C53/126 C08K5/09 C07C53/128

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP,A,0 010 807 (AKZO N.V.) 14 May 1980 see page 11, line 27 - line 38 see claim 1 ---	1-3,7
Y	US,A,3 730 943 (WEISFELD ET AL.) 1 May 1973 see column 2, line 32 - line 71 see column 3, line 44 - line 52 ---	1-3,7
A	WO,A,93 08246 (EXXON CHEMICAL PATENTS INC.) 29 April 1993 see claims 1-5 -----	1



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "I" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

27 September 1995

Date of mailing of the international search report

09.10.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Klag, M

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern. Application No

PCT/EP 95/02247

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0010807	14-05-80	CA-A- 1204755 JP-A- 55081834 JP-B- 63023980	20-05-86 20-06-80 18-05-88
US-A-3730943	01-05-73	AU-B- 463929 AU-B- 3342471 BE-A- 776712 FR-A- 2118659 BE-A- 686358 CH-A- 479642 DE-A- 1669802 FR-A- 1491749 GB-A- 1090017 NL-A- 6612162 US-A- 3567681	07-08-75 22-03-73 04-04-72 28-07-72 15-02-67 15-10-69 24-09-70 16-11-67 06-03-67 02-03-71
WO-A-9308246	29-04-93	AU-B- 660328 AU-A- 2692592 CA-A- 2121263 EP-A- 0609260 JP-T- 7500365	22-06-95 21-05-93 29-04-93 10-08-94 12-01-95